



# TECHNICAL DATA SHEET

TECHNICAL DATA SHEET  
A-A-2787 TY.I ENAMEL  
AEROSOL, LOW VOC  
PAGE 1 OF 2

**PRODUCT:** A solvent thinned, low VOC, aerosol enamel that meets specification A-A-2787 Type I.

**DESCRIPTION:** A-A-2787 TYPE I AEROSOL ENAMEL, LOW VOC is a high quality alkyd enamel available in gloss, semigloss and flat finishes.

**PROPERTIES:** COLORS..... Per Fed-Std 595B  
FINISH..... Gloss, Semigloss, Flat

**DRYING TIMES:**  
TO TOUCH..... Within 30 Minutes  
DRY THROUGH..... Within 18 Hours

**ADVANTAGES:**

- (1). Low "VOC"
- (2). Meets A-A-2787 Type I
- (3). Aerosol Spray Application
- (4). Air Dry Finish

**USES:**

- (1). Furniture
- (2). Equipment
- (3). Shelving
- (4). Industrial Facilities



# TECHNICAL DATA SHEET

TECHNICAL DATA SHEET  
A-A-2787 TY.I ENAMEL  
AEROSOL, LOW VOC  
PAGE 2 OF 2

## APPLICATION & REDUCTION:

Intrepid's A-A-2787 Enamels can be applied by conventional or airless spray application. For spraying, thin up to 10% or as needed with Xylene. For brushing, use as is or with minimum thinning with TT-T-306C Type I Reducer.

## SURFACE PREPARATION:

Surface must be clean, dry and free of all contamination before application. Prime and apply topcoat per specification instructions. If used on previously painted surfaces, coating must be reduced and tested on a small area for compatibility with the existing coating.

## STEEL:

Surface must be clean and free of all oil, grease and foreign material. Badly rusted or pitted steel should be cleaned by commercial sandblasting and primed the same day.

## PRECAUTIONS:

Contents are FLAMMABLE.

Keep away from heat and open flame.

KEEP OUT OF THE REACH OF CHILDREN.

Do not take internally.

Avoid breathing vapor or mist.

Do not use in tank or pit without proper protection.

Read Material Safety Data Sheet before use of this product.