



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET

A-A-3183

EXTERIOR LATEX

PAGE 1 OF 2

PRODUCT: A water-base, 100% acrylic latex paint for exterior and wood and masonry surfaces. This product is available in gloss (Type I), Semi-Gloss (Type II), Eggshell/Satin (Type III), and Flat (Type IV) finishes.

DESCRIPTION: An interior-exterior 100% acrylic latex paint with outstanding exterior durability. This coating can be applied to metal, masonry and wood surfaces. It is ideal for use on primed metal, surfaces that have been previously painted or properly prepared, and for use on clean concrete and wood. Self-priming on concrete, drywall, masonry and fiberboard. This acrylic coating is extremely versatile due to its rich formulation.

PROPERTIES: COLOR.....Full Spectrum
SOLIDS(Weight).....59 - 61%
SOLIDS(Volume).....44 - 46%
THEORETICAL COVERAGE.....640 mil sq.ft/gal
DRY FILM THICKNESS.....1.5 to 2.0 mils p/coat
DRYING TIME-AT 75 DEGREES F:
TO HANDLE.....30 Minutes
TO RECOAT.....2 Hours
VEHICLE TYPE.....Acrylic Latex
WEIGHT/GAL.....10.6 to 11.5 lbs/gal

ADVANTAGES: (1). Low Volatile Organic Compound Content.
(2). Excellent Exterior Durability.
(3). Excellent Foundation.
(4). Extremely Abrasion Resistant.
(5). Water Reducible.
(6). Water Clean-Up.
(7). High Solids.

USES: (1). Wood.
(2). Metal.
(3). Concrete.
(4). Masonry.
(5). Interior and Exterior.



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET

A-A-3183

EXTERIOR LATEX

PAGE 2 OF 2

APPLICATION & REDUCTION:

100% Acrylic Latex Coating can be applied by brush, roll or spray. For brushing and rolling, use as is or thin with Water. Use only nylon or synthetic bristle brushes. Use short nap synthetic covers for smooth surfaces. For rough surfaces, use long-nap synthetic covers. For spraying, thin up to 15% or as needed with Water. Use appropriate tip and atomizing pressure for equipment, weather conditions and applicator technique.

SURFACE PREPARATION:

Surface must be clean, dry and free of all contamination before application of primer.

STEEL:

Surface must be clean and free of all oil, grease and foreign material. Badly rusted or pitted steel should be cleaned by commercial sandblasting and primed the same day.

PRECAUTIONS:

KEEP OUT OF THE REACH OF CHILDREN.

Do not take internally.

Avoid breathing vapor or mist.

Do not use in tank or pit without proper protection.

Read Material Safety Data Sheet before use of this product.