



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
ELECTROSTATIC ALKYD ENAMEL
PAGE 1 OF 2

PRODUCT: A high quality, fast drying, low VOC alkyd enamel specifically formulated for electrostatic applications. This product is extremely durable with excellent flow and leveling characteristics.

DESCRIPTION: A specially formulated electrostatic industrial alkyd enamel. TriCom's Electrostatic Alkyd Enamels are durable, washable, easy to apply and have excellent hide and scrub properties.

PROPERTIES: COLORS..... Full Spectrum(All Colors)
SOLIDS(Weight)..... 59 - 71%
SOLIDS(Volume)..... 49 - 50%
THEORETICAL COVERAGE..... 450 sq.ft/gal*
DRYING TIME-AT 75 DEGREES F:
TO HANDLE..... 1 To 4 Hours
TO RECOAT..... 8 To 12 Hours
VEHICLE TYPE..... Modified Alkyd
WEIGHT/GAL..... 8.2 - 11.2 lbs/gal
* Coverage @ 1 Mil Dry Film.

ADVANTAGES: (1). Great for Electrostatic Applications
(2). Excellent Hide.
(3). Extremely Durable.
(4). Excellent Flow and Leveling.
(5). Easy Application.
(6). Extremely Washable.



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
ELECTROSTATIC ALKYD ENAMEL
PAGE 2 OF 2

APPLICATION & REDUCTION:

Intrepid's Electrostatic Alkyd Enamels are formulated for electrostatic spray application. For spraying, thin up to 15% or as needed with Xylene for proper flow and atomization specific to your spray equipment.

SURFACE PREPARATION:

Surface must be clean, dry and free of all contamination before application of electrostatic alkyd enamel.

PRECAUTIONS:

Contents are COMBUSTIBLE.

Keep away from heat and open flame.

KEEP OUT OF THE REACH OF CHILDREN.

Do not take internally.

Avoid breathing vapor or mist.

Do not use in tank or pit without proper protection.

Read Material Safety Data Sheet before use of this product.