



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
INTREPID URETHANE MODIFIED
ELASTOMERIC EXTERIOR LATEX
COATING
PAGE 1 OF 2

PRODUCT: A water-base, urethane modified, elastomeric coating with superior durability, flexibility, and UV resistance. This coating is weather and flame resistant.

DESCRIPTION: A urethane modified elastomeric coating formulated with a high quality acrylic elastomeric resin to provide excellent exterior durability and UV resistance. This coating can be used as a system for roofs along with fiberglass membranes and cloth. It has excellent flexibility for expansion and contraction resistance. Can be used over hairline cracks.

PROPERTIES:

COLOR.....	White
SOLIDS(Weight).....	60 - 65%
SOLIDS(Volume).....	50 - 55%
THEORETICAL COVERAGE.....	400 sq.ft/gal
ELONGATION.....	325 - 350%

DRYING TIME-AT 75 DEGREES F:

TO TOUCH.....	1 Hour
TO RECOAT.....	4 Hours
VEHICLE TYPE.....	Elastomeric/Acrylic
WEIGHT/GAL.....	12.2 to 12.4 lbs/gal

ADVANTAGES:

- (1). Low Volatile Organic Compound Content
- (2). Excellent Exterior Durability
- (3). Excellent Flexibility
- (4). Extremely Weather Resistant
- (5). Water Reducible
- (6). UV Resistant

USES:

- (1). Asphalt
- (2). Aluminum
- (3). Concrete
- (4). Polyurethane Roofs
- (5). Wood Roofs
- (6). Galvanized Steel



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
INTREPID URETHANE MODIFIED
ELASTOMERIC EXTERIOR LATEX
COATING
PAGE 2 OF 2

APPLICATION & REDUCTION:

Intrepid's Urethane Modified Exterior Latex coating is ready for use at packaged consistency. For brushing and rolling, use at packaged consistency. For spraying, thin only as needed for proper atomization (10-20%).

SURFACE PREPARATION:

Surface must be properly prepared, clean, dry, and free of all contamination before application. Cracks and imperfections must be patched, mildew removed, loose or peeling paint removed by sanding or scraping.

STEEL:

Surface must be properly prepared, clean, and free of all oil, grease and foreign material. Badly rusted or pitted steel should be cleaned by commercial sandblasting and primed the same day.

PRECAUTIONS:

KEEP OUT OF THE REACH OF CHILDREN.
Do not take internally.
Avoid breathing vapor or mist.
Do not use in tank or pit without proper protection.
Read Material Safety Data Sheet before use of this product.
Keep from freezing.