



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
INTREPID WATERBORNE ACRYLIC
PRIMER
PAGE 1 OF 2

PRODUCT: A high quality waterborne primer.

DESCRIPTION: A waterborne acrylic water reducible primer. It offers excellent early water resistance and a sound base for use as a waterbase primer for masonry, maintenance, drywall, and OEM finishes.

PROPERTIES:

COLOR.....	White
VOLATILE ORGANIC COMPOUNDS.....	50 g/l
SOLIDS(Weight).....	60-65%
SOLIDS(Volume).....	50 - 55%
FLASH POINT.....	> 300 Deg.F
THEORETICAL COVERAGE.....	400 mil sq.ft/gal
DRY FILM THICKNESS.....	2.0 to 2.5 mils p/coat

DRYING TIME-AT 75 DEGREES F:

TO HANDLE.....	10 - 15 Minutes
TO RECOAT.....	20 - 30 Minutes
VEHICLE TYPE.....	100% Acrylic
APPROX. WEIGHT/GAL.....	11 lbs/gal

- ADVANTAGES:**
- (1). Superior Corrosion Resistance
 - (2). Early Water Resistance
 - (3). Superior Base
 - (4). Excellent Flash Rust Resistance
 - (5). Low "VOC" Content
 - (6). Water Clean-Up



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
INTREPID WATERBORNE ACRYLIC
PRIMER
PAGE 2 OF 2

USES: (1). Dry wall
(2). Masonry

APPLICATION & REDUCTION:

Intrepid's Acrylic Primer can be reduced with water up to 20% by volume for spraying applications. For high build applications, however, they can be used as packaged. Thin as needed with water for smooth flow and leveling of the paint film. Apply at 3-4 wet mils per coat.

SURFACE PREPARATION:

Surface must be clean, dry and free of all contamination before application.

STEEL:

Surface must be clean and free of all oil, grease and foreign material. Badly rusted or pitted steel should be cleaned by commercial sandblasting and primed the same day. Galvanized and aluminum substrates must be properly cleaned before application.

PRECAUTIONS:

KEEP OUT OF THE REACH OF CHILDREN.

Do not take internally.

Avoid breathing vapor or mist.

Do not use in tank or pit without proper protection.

Read Material Safety Data Sheet before use of this product.

KEEP FROM FREEZING.