



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
LACQUER TOPCOAT
(MPI #'s 122, 123, and 124)
PAGE 1 OF 2

PRODUCT: A very high quality nitrocellulose lacquer with good working properties and flow. This lacquer originally was designed as an aircraft finishing material, but it is now specified wherever a quality nitrocellulose finishing lacquer is required. Available in gloss, semigloss and satin sheens.

PROPERTIES: COLORS..... Full Range
GRIND..... Not Under 7.0
PIGMENT CONTENT..... Not Under 45%
VISCOSITY(Reduced)#4 Ford Cup..... Not Over 20 Sec.
FINISH(at 60 Degrees)
Satin - MPI #122..... 10-30 Units
Semi-Gloss - MPI #123..... 35-60 Units
Gloss - MPI #124..... 80+ Units

DRYING TIME AT 75 DEGREES F:

DUST FREE: 3 - 5 MINUTES
DRY HARD: WITHIN 40 MINUTES

USES:

- (1). Interior Wood
- (2). Machinery
- (3). Steel Surfaces
- (4). Doors
- (5). Office Equipment
- (6). Computer Cabinets



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
LACQUER TOPCOAT
(MPI #'s 122, 123, and 124)
PAGE 2 OF 2

APPLICATION & REDUCTION:

Intrepid's Nitrocellulose Lacquer should only be applied by spray application due to its fast dry properties. Thin one part lacquer with approximately 2 parts of high quality Lacquer Thinner. Spray one tack coat followed by one full wet coat being sure to keep a "wet edge" for smooth finish.

SURFACE PREPARATION:

Surface must be clean, dry and free of grease, oil, chalk, dust, and other contaminants. Sand smooth and clean with tack rag or duster. Putty or caulk all holes, dents, scratches and splits after application of primer.

PRECAUTIONS:

Contents are FLAMMABLE.

Keep away from heat and open flame.

KEEP OUT OF THE REACH OF CHILDREN.

Do not take internally.

Avoid breathing vapor or mist.

Do not use in tank or pit without proper protection.

Read Material Safety Data Sheet before use of this product.