



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET MIL-P-52192B EPOXY PRIMER

PRODUCT DESCRIPTION:

A two-component, air-drying or baking, chemical resistant epoxy primer. Can be used for ferrous and non ferrous metals as well as other substrates.

TYPICAL PROPERTIES:

- (1). **COLORS**..... Iron Oxide
- (2). **SHELF LIFE**..... 1 Year From Date of Mfg
- (3). **DRYING TIME:**
 - Set-To-Touch: Within 10 minutes.
 - Dry Hard: Within 90 minutes.
 - Full Hardness: Within 24 Hours.
- (4). **POT LIFE:** 6 - 8 hours(77 Deg F)
- (5). **Gloss Value:** 50 maximum
- (6). **Mixing Ratio:** 4:1

APPLICATION AND REDUCTION:

Each of the two components should be thoroughly mixed separately . Mix at a ratio of 4 parts Component A to 1 part Component B by volume. Mix thoroughly and allow to stand 30 minutes before using. Pot life is normally six to eight hours at 77 Degrees Fahrenheit. Reduce with MIL-T-81772B Type II Thinner if required.

PRECAUTIONS:

Always read Material Safety Data Sheet before use.

Contents are Flammable

KEEP OUT OF THE REACH OF CHILDREN!