



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
MIL-V-12276D
PERMANENT RESIN COATING

PRODUCT DESCRIPTION:

A clear thermosetting phenolic baking varnish for surfaces of engine components and metal parts.

TYPICAL PROPERTIES:

COLOR..... Clear
SOLIDS(Volume)..... 35-40%

DRYING CYCLE:

After air drying for one hour, the coated parts should be baked at 325 Degrees F +/- 5 Degrees, however, the size and shape of the parts may require deviation from this schedule in order to obtain full cure and hardness.

APPLICATION AND REDUCTION:

Normal application is dipping or spraying at packaged viscosity. Apply to a dry film thickness of 0.5 to 0.7 mils. If necessary, thinning may be done with MIL-T-81772B Type 3 or MIL-T-18362 not to exceed 5% by volume.

STORAGE:

Store Indoors at room temperature.
Keep away from heat, sparks and open flame.
Read MSDS before use. For industrial use only.