



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET TT-P-26C FIRE-RETARDANT COATING

- PRODUCT:** A government specification, single component, fire-retardant paint formulated to meet TT-P-26C.
- DESCRIPTION:** **TT-P-26C** is a fire-retardant coating that is resistant to burning and flaming per ASTM D-1360 with a flame spread rating of not more than 25 and a smoke development rating of not more than 50.
- PROPERTIES:**
- | | |
|------------------------|------------------|
| COLORS..... | Per Fed-Std 595B |
| FINISH..... | Lusterless |
| FINENESS OF GRIND..... | 3 Minimum |
| SPECULAR GLOSS..... | 12 Maximum |
| LEAD CONTENT..... | 0.5 Maximum |
- DRYING TIMES:**
- | | |
|---------------|----------|
| TO TOUCH..... | 4 Hours |
| DRY HARD..... | 18 Hours |
- ADVANTAGES:**
- (1). Fire-Retardant Properties
 - (2). Meets TT-P-26C (PT-209C)
 - (3). Resistant to Burning
 - (4). Air Dry Lusterless Finish
- USES:**
- (1). Aerospace Applications
 - (2). Submarines
 - (3). Factories
 - (4). Industrial Facilities
- APPLICATION:** Apply by brush, roller or spray methods. For brush and roll, thin with Mineral Spirits Reduce at 10% by volume. For spray application, thin with Xylene at 10-15% by volume.