

"Our Coatings Fly All Over the World"

Intrepid Coatings, Inc. Technical Data Sheets

Miscellaneous Coatings

Intrepid Coatings 1910 East Riverview Drive Phoenix, AZ 85034 Phone: (602)243-3293 Fax: (602)268-6801 E-Mail: info@intrepidcoatings.com

TECHNICAL DATA SHEET 100% ACRYLIC LATEX 300G02 GRASS GREEN CONCENTRATE PAGE 1 OF 2

- **PRODUCT:** A water-base, 100% acrylic latex grass tint in concentrate form.
- DESCRIPTION: 100% acrylic А waterbase base, tint grass concentrate for use on dormant lawns. This material can be reduced with water at a ratio of 10 parts water to 1 part concentrate all the way up to 22 parts water to 1 part concentrate depending on operator preference. This grass tint is waterbase and contains no lead or chromates. Color is a pleasing, natural green tint that duplicates the richness of a lawn or turf that is fade resistant due acrylic latex resin base. Fast to drv properties reduce tracking and staining after application.

ADVANTAGES: (1). Low Volatile Organic Compound Content.

- (2). Excellent Exterior Durability.
- (3). Fast Dry Water Reducible
- (4). Weather and UV Resistant.
- (5). Lead & Chromate Free.
- (6). Highly Concentrated.
- (7). High Solids.
- **USES:** (1). Soccer Fields.
 - (2). Cemeteries.
 - (3). Residential Lawns.
 - (4). Turfs.
 - (5). Golf Courses.

TECHNICAL DATA SHEET 100% ACRYLIC LATEX 300G02 GRASS GREEN CONCENTRATE PAGE 2 OF 2

APPLICATION & REDUCTION:

Green Grass Concentrate Tint can be reduced from 10 parts water to 1 part concentrate up to 22 parts water to 1 part concentrate depending on operator preference. After dilution, material can be applied with a garden type pump pressure sprayer or airless paint rigs. For best results, grass should be dry before application to avoid further dilution and to aid absorption and dry time.

PRECAUTIONS:

KEEP OUT OF THE REACH OF CHILDREN.

Do not take internally.

Avoid breathing vapor or mist.

Do not use in tank or pit without proper protection.

Read Material Safety Data Sheet before use of this product.

KEEP FROM FREEZING.

TECHNICAL DATA SHEET 500V02 DUAL-ETCH

PRODUCT DESCRIPTION:

A multi-purpose metal cleaner, prepaint conditioner and rust remover. This product is formulated for use on ferrous metals, including steel. It will also remove light rust from chrome-plated substrates.

TYPICAL PROPERTIES:

(1).	SOLVENT Inorganic Acids
(2).	VISCOSITY Water-like
(3).	FINISH Clear liquid pretreatment

DIRECTIONS FOR USE:

Solution is ready for use as packaged. No dilution is necessary. Freely apply Dual-Etch with brush, mop or synthetic sponge to the substrate. Use steel wool on heavy rust and oily deposits until they have been dissolved. Always keep the surface wet while scrubbing with rag or steel wool. While surface is wet, flush well with water or rub down surface with rags that have been periodically rinsed in clean water until all residue is removed. Allow surface to dry before applying paint.

PRECAUTIONS:

AVOID CONTACT WITH SKIN, EYES OR CLOTHING.

CONTAINS ACID, USE PROPER SKIN & EYE PROTECTION.

USE WITH ADEQUATE VENTILATION.

KEEP OUT OF THE REACH OF CHILDREN.

IN CASE OF IRRITATION, FLUSH WITH LARGE AMOUNTS OF WATER.

READ MATERIAL SAFETY DATA SHEET BEFORE USING THIS PRODUCT.

TECHNICAL DATA SHEET EPOXY CRACK FILLER

PRODUCT: A liquid modified 100% solids epoxy coating with room temperature curing. Excellent adhesion to concrete and other materials. This coating will cure in the presence of moisture.

- **MAJOR USES:** Patching and surfacing, patching compounds, adhesives, bonding new and old concrete, potting and encapsulation, casting, hand lay laminating and seamless floors.
- PROPERTIES: 100% solids Tensile strength...... 400 - 500 PSI Tensile elongation..... D-638 Pot life at 77 F..... 15 - 35 minutes Chemical and acid resistance..... Excellent
- APPLICATION: Griggs Epoxy Crack Filler is supplied in kits that yield 1 gal. This material can be poured directly into the crack. Always remember to mix Part A with Part B. It is very important to mix both parts well before use. Also very important is the thorough mixing after combining part A with part B.
- **PRECAUTIONS:** Take these precautions before the coating dries and during application.

The following applies to Part A and Part B

Harmful or fatal if swallowed. Vapor harmful. Eye irritant. Keep away from heat, sparks, and open flame. Avoid prolonged contact with skin or breathing of vapors. Keep containers closed when not in use. In case of spillage, absorb and dispose of in accordance with local applicable regulations.

Use with adequate ventilation. KEEP OUT OF REACH OF CHILDREN!!! If swallowed do not induce vomiting. CALL A PHYSICIAN IMMEDIATELY.

TECHNICAL DATA SHEET 4606-100 EPOXY PAGE 1 OF 3

PRODUCT: A liquid modified 100% solids epoxy coating.

DESCRIPTION: ICS 4606-100 Epoxy Coating is a two-component epoxy coating that contains an extremely high solids content. When fully cured, it forms an extremely tough, glossy, blush- free film that exhibits excellent impact and abrasion resistance. The cured film is unaffected by grease, oil, gasoline, detergents, and most solvents. This epoxy coating is formulated to cure in the presence of moisture. ICS 4606- 100 Epoxy Coating can be applied at any mil thickness in a single application due to its high solids content. This coating may be made into a non-skid film by the addition of silica sand or any desired aggregate.

MAJOR USES: ICS-4606 100 Epoxy Coating can be used for concrete flooring and walls of containment reservoirs and seamless floors in garages carports, factories, warehouses and industrial facilities, sewage and waste treatment plants, water treatment plants.

PROPERTIES:

SOLIDS(Volume) 100%
TENSIL STRENGTH 9500-10000 PSI
TENSIL ELONGATION
COLOR Light Gray
POT LIFE(77 degrees F) 1-2 Hours*
TACK FREE 7 Hours*
RECOAT Overnight*
LIGHT SERVICE 24 Hours*
FULL SERVICE 5 Days*
GLOSS Full Gloss
VOC0
*Higher temperatures will accelerate dry times and
decrease pot life, lower temperatures will lengthen
cure times and slightly increase pot life.

TECHNICAL DATA SHEET 4606-100 EPOXY PAGE 2 OF 3

SURFACE PREPARATION: Surface to be coated must be clean, structurally sound and free of all foreign contaminants including dirt, wax, loose paint or curing compounds. Surface may be damp, but standing water must be removed. Concrete should be sandblasted (whip blast). If recoating an epoxy surface is desired, and coating has cured more than 24 hours at 77 degrees F or cannot be indented with a fingernail, a light sanding with 60 80 grit sandpaper is required for proper adhesion of the new coat.

MIXING INSTRUCTIONS: This material is 100% solids with high viscosity. Mix only that amount of material that can be used in a 2 Hour work period at 77 degrees F. Work times are shortened by higher temperatures. For longer pot life(work life) pour mixed material on floor immediately after mixing. Always carefully measure the amounts and mix for 2 full minutes using a wooden stir stick, scraping the bottom and sides of the mixing vessel. Thorough mixing of the material is very important for obtaining a properly cured film.

APPLICATION RECOMMENDATIONS: ICS 4606-100 EPOXY COATING can be applied by brush, roller, notched trowel or airless spray. It is normally applied as received. For application of high build protective coatings to concrete, normal spread rate is 200-300 square feet per gallon. At this spread rate, a dry film thickness of 6-8 mils and a uniform glossy film will be achieved. Application is most easily achieved by pouring the admixed material on the floor, brush trimming the edges and seams and spreading the material with a short nap or carpet roller. Backroll sufficiently to insure a good even distribution of the coating. If a non-slip surface is desired, walk back onto the uncured coating wearing golf shoes and sprinkle silica sand from a shaker can into the coating and roll it in with a short nap or carpet roller. When airless equipment is used, a 45 to 1 pump and .022" to .030 tip is recommended. DO NOT LET ADMIXED MATERIAL REMAIN IN OR ON APPLICATION EQUIPMENT LONGER THAN 2 HOURS.

TECHNICAL DATA SHEET 4606-100 EPOXY PAGE 3 OF 3

PRECAUTIONS:

USE WITH ADEQUATE VENTILATION.

KEEP OUT OF THE REACH OF CHILDREN.

USE WITH PROPER DUAL CARTRIDGE RESPIRATOR WITH GREEN BAND CARTRIDGE TO PROTECT AGAINST METHYL AMINE VAPORS.

AVOID SKIN CONTACT, WEAR PROTECTIVE GLOVES.

WEAR SAFETY GLASSES OR GOGGLES.

DO NOT BREATHE VAPORS.

READ MATERIAL SAFETY DATA SHEET BEFORE USING THIS COATING.

TECHNICAL DATA SHEET 4606 PATCH EPOXY PAGE 1 OF 2

- **PRODUCT:** A liquid modified 100% solids epoxy coating with room temperature curing. Excellent adhesion to concrete and other surfaces.
- **MAJOR USES:** Patching, filling joints and cracks, surfacing ramps and other industrial areas that require a non skid surface.
- **PROPERTIES:** 100% solids

Cure Time:

Light Traffic..... 4-12 hours Heavy Traffic..... 12-24 hours Resistant to..... Chemicals, Cleaning Solvents and Soaps, Jet Fuels, Degreasers and Solvents,

SURFACE PREPARATIONS:

The minimum cure time of concrete must be least 30 days before application of 4606 Patch Epoxy (concrete shrinks during the normal curing process and may continue to shrink and settle after the 30 day curing period). Ambient & surface temperature of substrate must be above 50 degrees F. for proper curing of 4606 Patch Epoxy. The crack or joint should be dry and free of all loose debris, dirt, dust, curing compounds, release agents and other contaminants to produce a sound surface before application of 4606 Patch Epoxy.

MIXING:

Mix Component A & B until all pigments and settlement are completely mixed in before combining the two components. Then slowly pour component B into component A mixing slowly. Mixed admixed material 1-2 1/2 minutes until completely mixed (if components A & B are not completely mixed this will severely effect the curing process of 4606 Patch Epoxy). Manual or mechanical mixing may be used to mix 4606 Patch Epoxy. Dispense admixed material and clean tools immediately

1343

TECHNICAL DATA SHEET 4606 PATCH EPOXY PAGE 2 OF 2

(cleaning may be done with T-262 Epoxy Thinner or a good Lacquer Wash). To extend the pot life of 4606 Patch Epoxy components A & B may be inserted into a freezer or ice bath before mixing the 2 components with each other.

- **APPLICATION:** 4606 Epoxy Crack Filler is supplied in kits. This material can be poured directly into the crack or applied with a bulk dispensing caulking gun. Always remember to mix Part A with Part B. It is very important to mix both parts well before use. Also very important is the thorough mixing after combining part A with part B. 4606 Patch Epoxy should be applied to joints and cracks in 2 stages. The first stage should fill the crack or joint approximately half the distance to the surface. Allow the first stage to settle 15 to 30 minutes then apply second stage until flush with the surface. All 4606 Patch Epoxy is filled over the surface should be shaved until flush with the surface.
- **PRECAUTIONS:** Take these precautions before the coating dries and during application.

The following applies to Part A and Part B

Harmful or fatal if swallowed. Vapor harmful. Eye irritant. Keep away from heat, sparks, and open flame. Avoid prolonged contact with skin or breathing of vapors. Keep containers closed when not in use. In case of spillage, absorb and dispose of in accordance with local applicable regulations.

<u>CAUTION:</u> <u>Admixed material may reach temperatures</u> <u>above 150 degrees F.</u> Use with adequate ventilation. KEEP OUT OF REACH OF CHILDREN!!! If swallowed do not induce vomiting. CALL A PHYSICIAN IMMEDIATELY.

TECHNICAL DATA SHEET BOILED LINSEED OIL

PRODUCT DESCRIPTION:

A 100% pure boiled linseed oil for use on wood furniture or as an additive to oilbase enamels.

TYPICAL PROPERTIES:

(1).	WEIGHT PER GALLON 7.82 - 7.85
(2).	SPECIFIC GRAVITY
(3).	PERCENT VOLATILE BY VOLUME
(4).	FLASH POINT GREATER THAN 200 F

DIRECTIONS FOR USE:

Use as a sealer and enhancer for wood and wood furniture. May also be used in some types of oilbase alkyd coatings to slow drying time and increase flow and leveling.

TECHNICAL DATA SHEET EPOXY/POLY ANTI-GRAFFITI HI-BUILD PAGE 1 OF 2

PRODUCT: A two-component epoxy-modified polyurethane antigraffiti coating system.

DESCRIPTION: Griggs Epoxy-Modified Polyurethane coating is a high solids chemically cured product that forms a film that is resistant to chemicals, solvents and abrasion. This product has excellent adhesion to most substrates and is designed to seal and protect all masonry surfaces against many types of graffiti and weathering. This coating is available in a 4:1 mixture for spray, brush and roll applications. It has a high solids content for excellent film build and low volatile organic compound content. A two coat system is recommended for proper protection. Apply first coat in order to seal the surface, second coat is applied to achieve a proper film build for protection.

PROPERTIES:

TECHNICAL DATA SHEET EPOXY/POLY ANTI-GRAFFITI HI-BUILD PAGE 2 OF 2

SURFACE PREPARATION: Surface to be coated must be clean, dry, and free of all foreign contaminants including grease, oil, dirt and loose paint or curing compounds. Dirt and dust are best removed with a stiff bristle brush and by compressed air. Grease and oil should be removed by cleaning with appropriate solvents such as mineral spirits, lacquer wash thinner or xylene. New masonry and concrete surfaces must be cured a minimum of 28 days before application. Prepare cement and concrete surfaces by acid washing with a solution of 1 part muriatic acid to 4 parts water. Always pour the acid into the water to avoid splattering. Pour onto cement surface, broom or brush in with a stiff bristle brush in order to achieve proper etching. Flush thoroughly with clean water, neutralize any remaining acid with a solution of ammonia and water, flush again with clean water. Let dry thoroughly.

APPLICATION: Mix 4 parts Component 1 to 1 part Component 2 by volume. Thin first coat up to 50% by volume(2-qts per gal/kit) to achieve proper penetration on bare masonry surfaces. Apply second coat with minimum thinning(up to 1-qt per gal/kit) for proper film build. Thin with Griggs Epoxy/Poly Reducer. This coating may be applied by brush, roll or spray methods.

PRECAUTIONS:

KEEP FROM REACH OF CHILDREN.

KEEP AWAY FROM HEAT, SPARKS OR FLAME.

USE WITH ADEQUATE VENTILATION.

AVOID BREATHING VAPOR OR MIST.

READ MATERIAL SAFETY DATA SHEET BEFORE USING.

TECHNICAL DATA SHEET GRIGGS EPOXY LOOP SEALANT

PRODUCT: A viscous, two component, liquid epoxy for inductive loops.

DESCRIPTION: Griggs Epoxy Loop Sealant is a high viscosity liquid epoxy formulated for use in sealing inductive wire loops and leads imbedded in asphalt, concrete and portland cement concrete for traffic signal controls and vehicle counters. This epoxy is used for repair work on existing spalls, cracks, and other deformations in and around saw cuts housing inductor loops and leads. The rapid cure allows minimum traffic delay. This sealant is suitable for use in freeze-thaw areas and can be used on grades up to 15 percent without excessive flow of material.

DIRECTIONS FOR USE: Saw cuts shall be blown clean and dry with compressed air to remove all excess moisture and debris. For repairing damaged saw cuts, all loose spalled material shall be cleaned away from saw cut, chipping back to sound asphalt concrete or portland cement concrete and all loose material cleaned from loop wires.

The mixing ratio is approximately 8.4# Component A to 1.4# Component B. Due to the impracticality of this ratio, packaging is premeasured. Open the resin Component "A" (the larger gallon can) and stir to reblend any settlement. If possible, pour into a larger mixing container such as a five gallon plastic pail. Add hardener can "B" and begin to slowly mix. Mix for 2 1/2 to 3 minutes until thoroughly blended with no streaking. No more material shall be mixed than can be used within 10 minutes from the time mixing operations are started.

CHARACTERISTICS:

Gel Time 13-18 minutes
Tensile Strength 400 psi(min)
Elongation
Shore D Hardness 45(min)

TECHNICAL DATA SHEET JM-3 STRIPPER

PRODUCT DESCRIPTION:

A mildly acidic viscous liquid paint remover developed especially for removing epoxy, polyurethane and other difficult industrial paint coatings from metal surfaces. Griggs JM-3 Stripper has long storage stability and excellent rinsing properties. It is not intended to be used in removing paint coatings from magnesium.

USAGE:

Griggs JM-3 Stripper comes ready to use and may be applied directly to metal surfaces. It may be sprayed, brushed or mopped onto the metal surfaces needing to be stripped of the paint coating. Do not use synthetic A natural bristle type is recommended. brushes. Apply JM-3 and allow to dwell for 15 to 30 minutes. When coating begins to blister, brush into a slurry and rinse with a pressure washer or steam gun. Slight rubbing while rinsing helps insure complete removal of paint residues.

WARNINGS AND PRECAUTIONS:

Griggs JM-3 Stripper contains methylene chloride and phenol. Use with adequate ventilation. JM-3 has a sharp acidic odor. Keep off skin and out of eyes. Keep away from heat, sparks and flame. Keep container tightly closed. For industrial use only. Read MSDS before using this product. Wear goggles and neoprene gloves when using this product. Keep out of reach of children.

TECHNICAL DATA SHEET LITOXY SEALER

PRODUCT DESCRIPTION:

Litoxy Sealer is formulated for corrosion control of magnesium and other metals.

TYPICAL PROPERTIES:

- (1). COLORS.....Yellow and Green
- (2). ELONGATION:

Passes 1/8" conical mandrel method per ASTM D-522-60.

- (3). WATER IMMERSION: No blistering, cracking, softening or delamination of film. No corrosion after 140+ hours in salt water 5% solution ASTM-B117.
- (4). MEK RUB: 100+ per ASTM D-740, PASSED
- (5). **IMPACT TEST:** Direct and reverse, 40 pounds, ASTM G-14 (06.01), PASSED.
- (6). CROSS HATCH TEST: 100%, ASTM D3359, PASSED
- (7). **FALLING SAND TEST:** OTTAWA SAND 20-30 MESH, ASTM D 968-81 METHOD A, PASSED.
- (8). HOT OIL TEST: MIL-L-7808 48 HOURS @ 300 oF, PASSED
- (9). **PENCIL HARDNESS:** 4H
- (10). Excellent Solvent, Chemical, Water & Heat Resistance.
- (11). Cures within 30 minutes at 350 degrees F.
- (12). Excellent Corrosion Resistance
- (13). WEIGHT/GAL: 10.1 lbs/gal
- (14). **SOLIDS(Volume):** 44-46%
- (15). SPRAYING VISCOSITY: 14-20 Seconds #2 Zahn Cup.

APPLICATION AND REDUCTION:

- (1). Allow part to cool if masking is required. High temperature tape shall be used.
- (2). Place part in oven and heat to 350 degrees F for 30 minutes.
- (3). Cool substrate to room temperature.
- (4). Adjust spray or dip consistency with T-60 Thinner. Use a minimum of 2 qts T-60 per gallon of Litoxy.
- (5). Coat all surface, both exterior and interior, to a thickness of .50 to 1.0 dry mil.
- (6). Air dry coating for 25-30 minutes, then bake in a preheated oven at 350 degrees F for 30 minutes minimum.
 Cool parts to room temperature and unmask as necessary.

1350

TECHNICAL DATA SHEET M-Y-R-A ADHESIVE EPOXY

- **PRODUCT:** A liquid modified 100% solids epoxy coating with room temperature curing. Excellent adhesion to concrete and other materials. This coating will cure in the presence of moisture.
- **MAJOR USES:** Flooring and surfacing, patching compounds, adhesives, bonding new and old concrete, potting and encapsulation, casting, hand lay laminating and seamless floors.
- PROPERTIES: 100% solids Tensile strength: 8,000 - 10,000 P.S.I. Tensile elongation: 6 - 7 Pot life at 77 F: 10 30 minutes. Chemical and acid resistance: Excellent (see manufacture for more details)
- MYRA Adhesive Epoxy is supplied in kits that 1 or APPLICATION: gallons. This material can be 5 rolled, squeegeed and brushed with proper tools. Mix part A with part B. It is very important to mix both parts well before use. Also very important is the thorough mixing after combining part A with part B. For longer pot life we suggest that after mixing well, admixed material be spread immediately to substrate. The thinner the mil the longer the pot life.

COLORS: Concrete Gray, some pastel colors upon request.

Take these precautions before the coating dries **PRECAUTIONS:** and during application. The following applies to Part A and Part B Harmful or fatal if swallowed. Vapor harmful. Eye irritant. Keep away from heat, sparks, and open flame. Avoid prolonged contact with skin or breathing of vapors. Keep containers closed when not in use. In case of spillage, absorb and dispose of in accordance with local applicable regulations. Use with adequate ventilation. KEEP OUT OF REACH OF CHILDREN!!! Ιf swallowed do not induce vomiting. CALL A PHYSICIAN IMMEDIATELY

TECHNICAL DATA SHEET TT-W-00572 TYPE SEALER PAGE 1 OF 2

PRODUCT: A clear, non-yellowing sealer formulated to meet Federal Specification TT-W-00572.

DESCRIPTION: Griggs TT-W-00572 clear sealer is а water repellent, penetrating sealer that will provide protection to any wood or concrete surface or Due to superior penetrating structure. its properties, exhibits excellent adhesion it to properly prepared substrates. This product is available is a full range of semi- opaque colors.

PROPERTIES:	COLORS Full Range
	FINISH Penetrating
	VEHICLE Butene Rubber
	SOLIDS(Volume) 12 - 16%
	WEIGHT/GAL 6.5 - 6.8#
	VISCOSITY 150 - 500 CPS
	DRYING TIMES:
	TO TOUCH 2 Hours

- ADVANTAGES: (1). Highly Durable. (2). Ultraviolet Resistant. (3). Penetrating.
 - (4). Oil Resistant.
 - **USES:** (1). Concrete Structures.
 - (2). Driveways.
 - (3). Wood.
 - (4). Railroad Ties.
 - (5). Plywood.
 - (6). Walkways.

TECHNICAL DATA SHEET TT-W-00572 TYPE SEALER PAGE 2 OF 2

- **APPLICATION:** Apply by brush, roller or spray methods. Use at packaged viscosity for all application methods. Clean up with Mineral Spirits.
 - **PRODUCT:** A clear, penetrating wood and concrete sealer.

PRECAUTIONS: Use with adequate ventilation.

Avoid contact with skin and eyes.

Do not take internally.

KEEP OUT OF THE REACH OF CHILDREN.

Vapor Harmful.

Wash hands after using.

TECHNICAL DATA SHEET WATERBASE POOL PAINT PAGE 1 OF 2

- **PRODUCT:** A water-reducible, rubber based swimming pool paint designed to withstand continuous submersion.
- **DESCRIPTION:** A waterbase swimming pool paint that is formulated using Goodyear rubberized resin. This coating is water thinnable, low-odor and meets air pollution regulations for Volatile Organic Compounds.

PROPERTIES:	COLORS Full Range
	GRIND Not Under 5
	GLOSS Flat & Gloss
	VISCOSITY 100 - 110 KU
	DRYING TIME-AT 75 DEGREES F:
	SET-TO-TOUCH Hour
	RECOAT TIME 4 Hours
	PVC54%
	SOLIDS(Weight)
	SOLIDS(Volume) 48%

- ADVANTAGES: (1). Water Clean-Up (2). Water Reducible (3). Low Odor (4). Meets VOC Regulations
 - (5). Fast Dry
 - **USES:** (1). Swimming Pools
 - (2). Fountains
 - (3). Concrete
 - (4). Plaster
 - (5). Ponds
 - (6). Reflection Basins

TECHNICAL DATA SHEET WATERBASE BASE POOL PAINT PAGE 2 OF 2

APPLICATION & REDUCTION:

Griggs Waterbase Rubber Pool Paint can be applied by brush, roller or airless spray application. For spraying, thin up to 10% or as needed with Water. For brush and roll use as is or with minimum thinning.

SURFACE PREPARATION:

Surface must be clean, and free of all contamination before application. Etch surface for best results. Surface may be damp but not wet prior to application. Consult your Griggs representative for specific surface preparation instructions. Allow 7 - 10 days of dry weather before filling pool. For each day of rain, allow 2 additional days of drying. Do not apply if rain threatens.

PRECAUTIONS:

KEEP FROM FREEZING.

KEEP OUT OF THE REACH OF CHILDREN.

Do not take internally.

Avoid breathing vapor or mist.

Do not use in tank or pit without proper protection.

Read Material Safety Data Sheet before use of this product.

#

#356 Polyurethane, 707 #4606 100% Solids Epoxy, 387 #4606 Patch Epoxy, 389

1

10% Polyurethane Accelerator, 498 100% Acrylic Emulsion VOC Free, 167 100% Acrylic Gloss Enamel, 177 100% Acrylic HD Block Filler, 33 100% Acrylic Latex, 2, 89, 109, 161 100% Acrylic Latex #1018, 230 100% Acrylic Latex Bug Stop Formula, 121 100% Acrylic Latex Elastomeric Textured Coating, 232 100% Acrylic Latex Exterior, 234 100% Acrylic Latex Flat, 19, 91, 93, 236 100% Acrylic Latex Gloss, 35, 95 100% Acrylic Latex Grass Green Concentrate, 1336 100% Acrylic Latex Interior, 107 100% Acrylic Latex Interior Gloss, 37 100% Acrylic Latex Masonry Filler, 238 100% Acrylic Latex Mildew Resistant, 97 100% Acrylic Latex Non-Sand Elastomeric Textured Coating, 240 100% Acrylic Latex Pearlescent Pigment, 242 100% Acrylic Latex Semigloss, 62, 99, 123 100% Acrylic Latex Semigloss Super Acrylic Series, 56 100% Acrylic Latex Textured Coating, 77 100% Acrylic Primer, 1253 100% Acrylic Stain, 101 100% Solids Conductive Epoxy, 392 100% Solids Epoxy, 396, 709 100% Super Acrylic Latex, 171

3

3-1 Stainout, 113, 244 36-603 Hi-Heat Coating, 712

4

4606 Patch Epoxy, 713, 1343 4606-100 Epoxy, 716, 1340

6

611BC Epoxy Amine Gloss Green Primer, 1155 611BC Epoxy Gloss Green Primer/Topcoat, 1147 611BC NPC61611 Epoxy Amine Coating Gloss Green, 719 612A Epoxy #34151 Green Primer, 1257 612A Epoxy Amine #34151 Green Primer, 1149 612A Epoxy Polyamine #34151 Green Primer, 1255

8

8865 Containment Epoxy Coating, 372, 599

A

A-423-66 Cati-Coat Epoxy Amine Coating, 720 A-423-66 Epoxy Amine Coating, 721 A-423-66 Epoxy Amine Coating #082 Munsell Blue, 705 A-423-66 Epoxy Amine Coating #17038 Gloss Black, 703 A-423-66 Epoxy Amine Coating Clear, 704 A-423-66 NPC61600-2 Epoxy Amine Coating, 722 A-423-66 NPC61624, NPC61678 Epoxy Amine Coating #16492 Gray, 706 A-932-66 Epoxy Enamel, 723 A-A-1452B Acid Resistant Lacquer, 724 A-A-1558A Stencil Paint, 725 A-A-1572 Lacquer Sanding Sealer, 1194 A-A-2246 Type I, Class 2, Latex Interior, 225 A-A-2246B Type I, Class 4, Latex Interior, 226 A-A-2336 Wood Primer, 1093 A-A-2787 Type I, Low VOC Aerosol Enamel, 726 A-A-2886A Type I, Traffic Paint, 399 A-A-2904 Mineral Spirits, 1327 A-A-2962 Type I, Class A, Alkyd Enamel Semigloss, 652 A-A-2962 Type I, Class A, Grade B, Alkyd Enamel Semigloss, 727 A-A-2962A Class A, Grade B, Alkyd Enamel Semigloss, 642 A-A-2962A Type I, Class B, Lusterless Alkyd Enamel, 664 A-A-2962A Type III, Class B, Alkyd Enamel Gloss, 728 A-A-3003 Spraying Lacquer, 729 A-A-3121 Rubberized Deck Enamel, 401 A-A-3164 Synthetic Lacquer, 731 A-A-3165 Lacquer Coating Gloss, 733 A-A-50574 Alkyd Enamel Semigloss, 223 A-A-59166 Walkway Compound Nonslip, 735 A-A-665E Fast Dry Aerosol Enamel, 736 A-A-857B Dope and Lacquer Thinner, 1323 Able Ratmoore Series, 968 Acrylic Abatement Coating, 75 Acrylic Block Filler, 105 Acrylic Coating Exterior, 342, 344, 346, 348, 352 Acrylic Enamel, 541, 737 Acrylic Enamel Interior, 246 Acrylic Enamel Primer, 942 Acrylic Hi-Gloss Latex Enamel, 175 Acrylic Pool Deck Coating, 326 Acrylic Lacquer Very Low VOC, 701 Acrylic Latex Flat, 145, 147 Acrylic Latex Flat Exterior, 149 Acrylic Latex Flat Interior/Exterior, 151 Acrylic Latex Primer, 69, 117, 1139

Acrylic Latex Semigloss, 4 Acrylic Latex Semigloss Enamel, 125, 127, 137 Acrylic Latex Stain, 103 Acrylic Masonry Stain, 209, 248 Acrylic Masonry Stain/Sealer, 356, 403, 405 Acrylic Primer, 990 Acrylic Urethane Enamel, 530 Acrylic Urethane Varnish, 23 Acrythane Acrylic Polyurethane, 739 ADOT #1 Alkyd Light Gray Primer, 964 ADOT #1 Phenolic Light Gray Primer, 966 ADOT #2 Off White, 15 ADOT #2 Off White Primer, 1083 ADOT #3 Hydro-Acrylic Aluminum Topcoat, 511 ADOT #3 Hydro-Acrylic Coating, 521 ADOT #3 Silicone Alkyd Enamel, 250, 743 ADOT #3 Topcoat Gloss, 741 ADOT #5 Aluminum, 548 ADOT #5 Hydro-Acrylic Aluminum Topcoat, 513 ADOT Hydro-Acrylic Primer, 1123, 1127, 1129, 1131 Alkyd Ceiling Enamel, 215 Alkyd Chalk-Bond Clear Primer, 1011, 1013 Alkyd Chalk-Bond Primer White, 1113 Alkyd Dipping Advance Gray Primer, 997 Alkyd Dipping Primer Advance Gray, 507 Alkyd Enamel High Gloss, 589, 745 Alkyd Enamel High Gloss Exterior, 591 Alkvd Enamel High-Gloss, 217 Alkyd Enamel Oilbase, 252 Alkyd M. W. Gray Primer, 1001 Alkyd Metal Primer, 944 Alkyd Metal Undercoat, 1105 Alkyd Primer Interior/Exterior, 254 Alkyd SSP 25 Lee Gray Primer, 1007 Alkyd Trim Enamel, 211 Alkyd Undercoat Interior, 1107, 1258 Alkyd Undercoat Interior/Exterior, 1087 Alkvd Varnish Clear, 256 AMS-3170 Graphite Varnish Thinner, 1321 Anti-Static Epoxy Polyamide Coating, 747 AP-561 Type JM-3 Stripper, 1328 Aquacom Waterbase Lacquer, 519 Aquacom Waterbase Sanding Sealer, 517 Aqua-Poly Waterborne 2-Part Polyurethane, 748 Aqua-Poly Waterborne 2-Part Polyurethane Clear, 300 Aqua-Star Series Waterbase Pool Paint, 749 Aqueous Undercoater, 1260 Aromatic Water-Borne Urethane Coating, 751

B

B-60 Acrylic Solvent Base Coating, 562 Baking Enamel Reducer, 1324 Block Out Lacquer #37038 Flat Black, 654 Boiled Linseed Oil, 1345 Bucellatone, 1304 Butoxy 33RC, 754

С

C-1178-66 Type Catalyst, 616 C-252-66 Type Catalyst, 619 C740 Flat Black Primer, 1233 C740 Water Reducible Lead-Free Alkyd Enamel, 694 Ceramicoat, 31 Ceramicoat Elastomeric Heat Shield Coating, 258, 756 Chlorinated Polymer Traffic Paint, 407 Chlorinated Rubber Metal Primer, 1047 Chlorinated Rubber Primer, 946 Corrosion-Guard Urethane Coating, 409

D

D202 Rust Conversion Primer, 1121 Damp Proof Slow-Dry Red Oxide Primer, 1037 DC202 Rust Conversion Primer, 1075 DC3 Surface Sealer, 758 DC6571-805 High Heat Aluminum Coating, 759 DC6571-805 Hi-Heat Aluminum Coating, 550 DC701 Water Reducible Acrylic Enamel High Gloss, 680, 761 DC701 Water Reducible Acrylic Gray Primer, 1210 DC701 Water Reducible Acrylic Primer, 1212 DC701 Water Reducible Acrylic Red Oxide Primer, 1214 DC733 Epoxy Amine Coating #082 Munsell Blue, 615 DC733 Epoxy Amine Coating NPC61661 FP5025 Type II, Class A, #17038 Gloss Black, 604 DC733 Epoxy Polyamine Coating, 610, 622, 763 DC733 Epoxy Polyamine Coating #011 White, 620 DC733 Low VOC Epoxy Polyamine Coating, 628 DC733 Low VOC Epoxy Pool Paint, 632, 765 DC7337 Series Waterborne Acrylic Urethane Enamel, 334, 411, 536 DC740 ADOT #1 Light Gray Primer, 1125 DC740 ADOT #2 Off White Primer, 1250 DC740 Agate Brown Oxide Primer, 1241 DC740 Bunger Red Oxide Primer, 1243 DC740 Bunger Red Primer, 1065 DC740 Dipping Enamel Gray, 682 DC740 Ferro Prime Gray, 1228 DC740 Primer, 1235 DC740 Ratmoore #1 Primer, 1218 DC740 Ratmoore #4 Water Reducible White Primer, 1245 DC740 Ratmoore #7 Water Reducible Gray Primer, 1220 DC740 Ratmoore Primer, 1056, 1216, 1262 DC740 Semigloss Convey Red Oxide Primer, 1239 DC740 SSPC Ratmoore Primer, 1069 DC740 Water Reducible #124042 Flat Black, 684 DC740 Water Reducible Able White Primer, 1247 DC740 Water Reducible Modified Enamel, 688 DC740 Water Reducible Modified Enamel #450 Tan, 686 DC740 Water Reducible Ratmoore TN Gray Primer, 1230 DC740 Water Reducible Western Fab Gray Primer, 1225 DC740 Water Reducible White Primer, 692 DC740 Waterborne Wood Stain, 260, 767 DC740 Western Fab Gray Industrial Primer, 1223

DC740ML Water Reducible Modified Enamel, 690 Deer Valley Enamels, 579, 583 Deer Valley Enamels Semigloss Matthews White, 585 Deer Valley Gray Primer, 956 Deer Valley Quick-Dry Aluminum, 575 Diamond Rust Shield Red Primer, 1058 DOD-24607 Non-Flaming Enamel, 670 DOD-24607A Non-Flaming Enamel, 674 DOD-P-15328C Pre-Treat Wash Primer, 1023 DOD-P-21035A Zinc Compound, 1186 Dual-Etch, 1300, 1338

Е

EB. 1329 Eggshell Alkyd Enamel, 262 Elastomeric Acrylic Tire Refurb Paint, 525 Elastomeric Canvas Coating, 66 Elastomeric Coating, 41, 58, 264 Elastomeric Coating #4606, 47 Elastomeric Coating Utility Elasto-Black, 17 Elastomeric Epoxy Sealer, 1264 Elastomeric Prime Coat Adhesive White, 64 Elastomeric Primer, 39, 119 Elastomeric Roof Coating, 43, 45 Elastomeric White Primer, 319, 1135 Elastopox Coating, 6 Elastowall Coating, 52 Electrostatic #7 Gray Primer, 976 Electrostatic (611BC) Epoxy Primer, 769 EMS52438 K0548 Type NPC61270-1 Graphite Varnish G8450, 554 Enviro-Gard 100% Solids Epoxy Coating, 367 Epoxy Crack Filler, 366, 597, 1339 Epoxy Elastomeric Sealer, 413 Epoxy Ester Alkyd Enamel Low VOC Hi-Solids, 772 Epoxy Ester Primer, 978 Epoxy Hi-Build Pool Paint, 785 Epoxy Loop Sealant, 415, 774, 1348 Epoxy Modified Polyurethane Coating, 298, 495 Epoxy Polyamide Coating, 775 Epoxy Polyamide Coating Fluorescent Finish, 777 Epoxy Polyamide Coating Hi-Build, 779 Epoxy Polyamide Hi-Build Topcoat, 625 Epoxy Polyamide Red Oxide Primer, 1043 Epoxy Polyamide Topcoat Hi-Build, 781 Epoxy Polyamide Zinc Dust Primer, 1143 Epoxy Polyamine Coating Metallic Series, 630 Epoxy Polyamine Topcoat Hi-Build, 783 Epoxy Pool Paint Primer White, 416 Epoxy Pool Paint White Primer, 1266 Epoxy Spot Sealer Clear, 608 Epoxy White Primer, 1165 Epoxy Zinc Rich Primer, 986 Epoxy/Poly Hi-Build Anti-Graffiti, 770, 1346 Exterior Graffiti Block-Out Paint, 153 Exterior Wood Primer, 111

\mathbf{F}

Fast Dry Water-Reducible Primer, 992 Ferro-Prime #36375 Steel Gray, 999 Fire Resistant Paint White, 49 Fire Resistant Sealer Clear, 187 Fire Retardant Coating, 115 Fire Retardant Primer Waterbase, 266 Flat Alkyd Enamel, 543 Flexi-Coat Rubberized Elastomeric Coating, 787 Flexocryl Coating, 323 Flexocryl Floor and Deck, 305, 328 Floor and Deck Enamel, 364 FP5025 Type I, Class C, 611BC Epoxy Amine Gloss Green Primer, 1148 Franciscan Brown Primer, 1025

G

G & G 305 Epoxy Coating, 789 Galvanized Metal Primer, 1101 Gila Coat Asphaltic Coating, 792 Graffiti-Guard Polyurethane Clear, 487 Gym Finish Varnish, 418

Η

HAPS Free Acrylic Gloss Clear, 555 Hi-Build Acrylic Polyurethane, 485 Hi-Build Epoxy Polyamide Primer, 1045, 1099, 1109 Hi-Build Epoxy Polyamine Primer, 1268 Hi-Build Latex Paint, 8 Hi-Gloss Alkyd Enamel, 268 Hi-Heat Coating, 552, 553 Hi-Heat Coating #17038 Gloss Black, 539 Hi-Heat Coating 1000 Degrees, 794 Hi-Heat Coating 1200 Degrees, 795 Hi-Heat Coating 800 Degrees, 793 Hi-Heat Emissive Coating, 538 Hinge Packs Touch-Up Kits, 803 Hi-Solids Moisture-Cure Zinc Rich Primer, 980 Hi-Solids Polyurethane, 420, 796 Hi-Solids Polyurethane 2-1, 423 Hi-Solids Polyurethane Fluorescent Finish, 799 Hi-Solids Polyurethane Metallic Series, 801 Hydro-Acrylic #3 Topcoat, 15 Hydro-Acrylic ADOT #1, 15 Hydro-Acrylic ADOT #1 Red Oxide Primer, 1071 Hydro-Acrylic Coating, 25, 426 Hydro-Acrylic Stain, 27 Hydro-Acrylic Stain #30318, 303 Hydro-Acrylic Stain Calle De Rio, 29 Hydropox #1 Curb Red, 379 Hydropox #1 DTM Acrylic Enamel High Gloss, 804 Hydropox #1 Floor Coating, 428 Hydropox #1 Marking Paint, 431 Hydropox #1 Waterborne, 806 Hydropox #1 Waterborne Primer, 1174

Hydropox #2 4-1 Epoxy, 433, 808 Hydropox #2 4-1 Epoxy Masonry Coating, 438 Hydropox #2 4-1 Epoxy Utility Coating, 445 Hydropox #2 Epoxy Primer, 1171 Hydropox #2 Flexocryl, 219, 270 Hydropox #3B Waterborne, 810

I

Industrial Alkyd Enamel Flat Clear, 595 Industrial Alkyd Primer Western Fab Gray, 988 Industrial Dipping Enamel, 545 Industrial Machinery Enamel Semigloss, 587, 593 Industrial Oilbase White Primer, 1079 Injection Epoxy Filler, 450 Inorganic Zinc Rich Reducer, 1319 Interior Acrylic Enamel Eggshell Finish, 9 Interior Latex Flat, 11 Interior Latex Semigloss, 13 Isopropyl Alcohol, 1303

J

Jet-Dri Gray Primer, 962 JM-3 Stripper, 1330, 1349

L

Lacquer Sanding Sealer, 227, 696 Lacquer Topcoat, 228, 697, 699 Latex Blended Acrylic, 81, 83, 85, 87 Latex Blockout White, 1103 Latex Dry Fall Coating, 51 Latex Flat, 60, 67, 73, 79, 165, 169 Latex Flat Exterior, 157 Latex Sego-Acrylic Primer, 1270 Latex Semigloss Enamel, 129, 139, 141 Latex Semigloss Enamel Exterior, 143 Latex Semigloss Exterior, 131 Latex Semigloss Interior, 133 Latex White Primer, 1272 Litoxy Sealer, 812, 1350 Log Oil Wood Sealer Clear, 193 Long Oil Alkyd Flat, 207 Low VOC Epoxy Polyamine Coating, 1176 Low VOC Fab Gray Industrial Primer, 1005 Low VOC Lead Free Epoxy Polyamine Primer, 1178 Low VOC Quick Dry Enamel, 813 Low VOC Quick-Dry Enamel, 573, 577 Low VOC Quick-Dry Enamel Close Blue, 581 Low VOC Universal Phenolic-Alkyd Metal Primer, 1049

Μ

M. W. Alkyd Red Oxide Primer, 1073 Maincote Acrylic Enamel, 534 Masonry Acrylic Coating Flat Clear, 350

MCS6074D Aerosol Enamel Black, 815 Metal Pretreatment Wash Primer, 1015 Metal Weld Ratmoore Red Oxide Primer, 1067 Metallic Series Acrylic Coating, 816 Metallic Series Industrial Alkyd Enamel, 818 Methacrylate Acrylic Lacquer Clear, 452 MIL-A-6091 Denatured Alcohol, 1322 MIL-C-17504C Acrylic Coating Clear, 661 MIL-C-22750D Type I and II, Epoxy Polyamide Coating, 820 MIL-C-22750F Epoxy Hi-Solids Coating, 821 MIL-C-22750F Type I and II, Epoxy Polyamide Coating, 612 MIL-C-450C Bituminous Coating, 651, 653, 822 MIL-C-46168D Polyurethane, 823 MIL-C-46168D Type IV, 825 MIL-C-81773C Polyurethane, 479, 827 MIL-C-83286 Polyurethane RAL-6021 Green, 493 MIL-C-83286B Catalyst, 497 MIL-C-83286B Polyurethane, 829 MIL-C-83286B Polyurethane Coating, 483 MIL-C-85285B(AS) 4-1 Polyurethane Catalyst, 499 MIL-C-85285C Polyurethane, 831 MIL-DTL-15090D Formula 111 Equipment Enamel Light Gray, 833 MIL-DTL-24441/20 #150 Green Primer, 1160 MIL-DTL-24441/21A #151 Haze Grav. 598 MIL-DTL-24441/22A #152 White, 627 MIL-DTL-24441/23A Black Topcoat, 605 MIL-DTL-24631 Type II, 648 MIL-DTL-24631/1C Black Epoxy Coating, 650 MIL-E-11195E Fast Dry Enamel, 834 MIL-E-15090C Formula 111 Equipment Enamel, 836 MIL-E-16663A Enamel Semigloss, 634 MIL-E-22118B Electrical-Insulating Enamel, 671 MIL-E-24635B Silicone Alkyd Enamel, 640 MIL-E-52891B(ME), 838 MIL-E-5558A Type I, Wrinkle Finish Paint, 840 MIL-E-7729B Alkyd Enamel Gloss, 842 MIL-L-10287B Cellulose Nitrate Lacquer, 844 MIL-L-19537C Acrylic Nitro Cellulose Lacquer Gloss, 845 MIL-L-19537C Acrylic Nitro-Cellulose Lacquer Gloss, 675 MIL-L-19538C Acrylic Nitro-Cellulose Lacquer Camouflage, 847 MIL-L-46159A Low Reflective Acrylic Lacquer, 849 MIL-L-52043C Lacquer Semigloss, 851 MIL-L-81352A Acrylic Lacquer, 853 MIL-L-81352B Type I, Acrylic Lacquer, 855 MIL-L-81352B Type III, Polyurethane, 857 MIL-P-11414E Red Oxide Primer, 1202 MIL-P-14105D Heat Resisting Coating, 859 MIL-P-15930C Comp. G, Vinyl Zinc Chromate Primer, 1195 MIL-P-21035B Zinc Dust, 1184, 1189 MIL-P-21563B Fluorescent Paint, 662 MIL-P-21600A Fluorescent Paint, 861 MIL-P-22332B Comp. G, Zinc Chromate Primer, 1204

- MIL-P-22332B Zinc Chromate Primer, 1206
- MIL-P-23377F Type I and II, Epoxy Polyamide Coating, 862
- MIL-P-23377F Type I and II, Epoxy Polyamide Primer, 1274
- MIL-P-23377G Class C, Epoxy Polyamide Primer, 1275
- MIL-P-23377G Class N, Non-Chromate Formulation Epoxy Polyamide Primer, 1019
- MIL-P-24380B(SH), 645
- MIL-P-24441/20(SH) #150 Green Primer, 1156
- MIL-P-24441A(SH) #150 Green Primer, 1157
- MIL-P-26915B Class B, Zinc Dust Primer, 1276
- MIL-P-26915B Type I, Class B, Zinc Dust Primer, 1180
- MIL-P-26915B Type I, Zinc Dust Primer, 1182
- MIL-P-28577B Waterborne Acrylic Red Oxide Primer, 1198
- MIL-P-38336 Inorganic Zinc Rich Primer, 974
- MIL-P-46105 Zinc Rich Primer, 1278
- MIL-P-52108A Stencil/Obliterating Paint, 665
- MIL-P-52192B Epoxy Primer, 863
- MIL-P-53022B Epoxy Polyamide Primer, 864
- MIL-P-53022B Epoxy Primer, 1280
- MIL-P-53022B Type I, Epoxy #26622 Gray Primer, 1188
- MIL-P-53022B Type II, Epoxy #26622 Gray Primer, 1191
- MIL-P-53030 Primer, 1161, 1163, 1169
- MIL-P-53030A Water Reducible Epoxy Primer, 1145, 1281
- MIL-P-85582C Waterborne Epoxy Primer, 1153
- MIL-P-8585A Zinc Chromate Primer, 1196
- MIL-PRF-22750F Hi-Solids Low VOC Epoxy Coating, 865
- MIL-PRF-23377G Class C, Epoxy Polyamide Primer, 1283
- MIL-PRF-23377G Class N, Epoxy Polyamide Primer, 1115
- MIL-PRF-23377H Class C, Epoxy Polyamide Primer, 1119
- MIL-PRF-23377H Class N, Non-Chromate Formulation Epoxy Polyamide Primer, 1022
- MIL-PRF-23377H Type I, Class C, Epoxy Polyamide Primer, 1118
- MIL-PRF-24635B Silicone Alkyd Enamel, 643
- MIL-PRF-24635C Type II, Class 2, Silicone Alkyd
- Enamel, 678, 866
- MIL-PRF-26915D Type I, Class A, Zinc Dust Primer, 1284
- MIL-PRF-26915D Type I, Zinc Dust Primer, 1192
- MIL-PRF-3043C Permanent Resin Coating, 868
- MIL-PRF-81352B Type I, Acrylic Lacquer, 869
- MIL-PRF-81352B Type III, Polyurethane, 871
- MIL-PRF-85285C Polyurethane, 503, 873
- MIL-PRF-85285C Polyurethane Coating, 481
- MIL-PRF-85285D Class H, 875
- MIL-PRF-85285D Type I, Class H, 877
- MIL-PRF-85582C Waterborne Epoxy Primer, 1158
- MIL-PRF-85582D Waterborne Epoxy Primer, 1286
- MIL-R-3043B Permanent Resin Coating, 669
- MIL-T-19544E Acrylic Thinner, 1311
- MIL-T-6095B, 1331
- MIL-T-81772B Type I, Polyurethane Thinner, 1306
- MIL-T-81772B Type II, Epoxy Thinner, 1310
- MIL-T-81772B Type III, Polyurethane Thinner, 1318

MIL-V-12276D Type II, Phenolic Baking Varnish, 660
MIL-V-16399A Type B, Moisture Proof Varnish, 659
MIL-V-173C, 879
MIL-W-5044C Nonslip Walkway Compound, 880
Mineral Spirits, 1312
Moisture Cure Polyurethane, 489
Moisture-Cure Zinc Rich Primer, 972
MPI #28 Marine Spar Varnish Exterior Gloss Clear, 221
MPI #32 Traffic Paint, 454
Multi-Purpose Primer, 948, 1089
M-Y-R-A Adhesive Epoxy, 456, 881, 1351

Ν

- Nitrocellulose Lacquer, 883 Non-Skid Coating, 272, 457 Non-Skid Epoxy Coating, 613 Non-Skid Floor Coating Roughcoat, 459 Non-Skid Oilbase Coating, 461 NPC61612-2 612A Epoxy Amine #34151 Green Primer, 1151
- NPC61646 Wipecoat #6 Epoxy Amine Green, 1152

0

Oilbase Wood Stain Exterior, 179 Oilbase Wood Stain Interior, 181

Р

- P-415A-66 Epoxy Gray Primer, 1141
- P-415A-66 FP5025 Type I, Class A, E, C, MCS9010 Epoxy #34151 Green Primer, 1288
- P-415A-66 W/C-415A-66 Converter Epoxy #34151 Green Primer, 1252

P-674-66 Gray Primer, 958

- PCS5401 Type I, Class A, Epoxy Amine Primer, 1173
- Pigmented Concrete and Wood Sealer Semi-Transparent Brown, 301
- Polypane Polyurethane, 885
- Polyrock CF Crack Filler, 377
- Polyurethane Alkyd Enamel, 569
- Polyurethane Alkyd Enamel Semigloss, 213
- Polyurethane Coating, 505
- Polyurethane Gloss Interior/Exterior, 191
- Polyurethane Satin Varnish, 189
- Polyurethane Varnish Clear, 274
- Pool Paint Thinner, 1316
- Portland Cement Primer, 1091
- Protector Silicone Sealer Clear, 201

Q

Quick Dry Exclusive Gray Primer, 982 Quick Dry Therma Gray Primer, 1003 Quick-Dry Baking Enamel, 556 Quick-Dry Epoxy Primer, 1167

R

Ratmoore #2AS Red, 1039 Ratmoore #4 White Primer, 1097 Ratmoore #5 Gray Primer, 994 Ratmoore 200LCF Series Primer, 1289 Ratmoore Maricopa Red Primer, 1060 Ratmoore Primer, 950, 1054, 1085 Ratmoore Primer 1990 Revision, 952 Renoozit DC7337 Urethane Acrylic Coating, 887 Rock Lock Clear, 310 Rubber Base Sealer, 276 Rust-Gard Red Oxide Primer, 1063

S

Sealer White Primer, 1081 Semigloss Alkyd Enamel, 183 Semigloss Enamel, 563 Sharon Ratmoore White Primer, 1095 Shop Coat Red Oxide Primer, 1031 Silicone Alkyd Enamel Hi-Heat, 565 Silicone Alkyd Enamel Tempe Bronze, 559 Simulated Metallic Series Waterbase Acrylic Coating, 889 Spar Varnish Alkyd Resin, 185 Spar Varnish Gloss Clear, 195 Spar Varnish Phenolic Resin, 197 Special Shop Coat Red Oxide Primer, 1052 SSPC-11 Red Oxide Primer, 1029 SSPC-20 Type IC, Inorganic Zinc Rich Primer, 984 SSPC-Paint 25 Red Oxide Primer, 1041 Standard Set Epoxy Adhesive, 617 Sunguard Elastomeric Roof Coating, 71 Superflex Floor and Deck, 338 Synthetic Reducer, 1308

Т

T-120-66 Wash Primer Thinner, 1307 T-262A-66 Epoxy Thinner, 1313 T-77 Butoxy Thinner, 1301 Tar Guard Additive, 561 Tennis Court Coating, 315 Toluidine Red Tint #0725, 540 TPD-24607 Non-Flaming Enamel, 668 Tree Trunk Paint, 155 Triad Special Red Oxide Primer, 1077 TT-C-542E Moisture Cure Polyurethane Clear, 491 TT-C-542E Moisture Cure Urethane Clear, 657 TT-E-001384 Acrylic Enamel, 891 TT-E-1593B Silicone Alkyd Enamel, 912 TT-E-485F, 893 TT-E-485F Comp. G, 663 TT-E-487E Floor and Deck Enamel, 463 TT-E-489G Class A, Alkyd Enamel Gloss, 894 TT-E-489H Alkyd Enamel Gloss, 896 TT-E-489J Alkyd Enamel Gloss, 898 TT-E-490E Silicone Alkyd Enamel, 900

TT-E-508C Alkvd Enamel Semigloss, 278 TT-E-509C Type I, Class 1, Alkyd Enamel Odorless Semigloss, 280 TT-E-515A Quick Dry Enamel, 902 TT-E-516A Quick Dry Enamel, 904 TT-E-527C Lusterless Alkyd Enamel, 906 TT-E-527D Lusterless Alkyd Enamel, 907 TT-E-529 Alkyd Enamel Semigloss, 908 TT-E-529G Alkyd Enamel Semigloss, 910 TT-E-529G Type II, Alkyd Baking Enamel, 646 TT-E-751C Ethyl Acetate, 1332 TT-L-20A Lusterless Lacquer, 914 TT-L-32A Cobblestone Semigloss, 666 TT-L-32A Lacquer Gloss, 672, 916 TT-L-50E Type I, Lacquer, 918 TT-L-50G Type II, Lacquer, 919 TT-L-58E Lacquer Gloss, 637 TT-M-261 Methyl Ethyl Ketone, 1305 TT-N-95B Aliphatic Naphtha, 1320 TT-N-97C Type II, Aromatic Naphtha, 1325 TT-P-102E Alkyd Enamel, 287 TT-P-102F Long Oil Alkyd Enamel, 923 TT-P-110C Type I, Traffic Paint Black, 340 TT-P-115F Type I, Traffic Paint, 360 TT-P-115F Type II, AMD. 2, Traffic Paint, 384 TT-P-115F Type II, Traffic Paint, 358 TT-P-1411A Cementitious Paint, 677 TT-P-1511B Latex Semigloss Enamel, 135 TT-P-1757A Zinc Chromate Primer, 1208, 1291 TT-P-1757A/P-759A-66 Zinc Chromate Primer, 1017 TT-P-1757B Type I, Class C, Aerosol Zinc Chromate Primer, 941 TT-P-1757B Type I, Class C, Zinc Chromate Primer, 1293 TT-P-1757B Type I, Class N, Non-Chromate Primer, 1116 TT-P-1757B Type II, Class C, Zinc Chromate Primer, 1020 TT-P-1952B Waterbase Traffic Coating, 471 TT-P-1952C Waterbase Traffic Coating, 473 TT-P-1952D Waterbase Traffic Coating, 475 TT-P-19D Acrylic Latex, 281 TT-P-26C Fire Retardant, 283 TT-P-26C Fire-Retardant Coating, 649 TT-P-2756A Polyurethane Coating, 925 TT-P-28G Hi-Heat Coating, 547 TT-P-320D Aluminum Pigment, 924 TT-P-38E Aluminum, 635 TT-P-54C Acid Resistant Lacquer, 920 TT-P-636 Type Vulcraft Gray Primer, 970 TT-P-636D Red Oxide Primer, 1033 TT-P-641G Type III, Zinc Primer, 960 TT-P-645A Zinc Chromate Primer, 1027 TT-P-664D Red Oxide Primer, 1035 TT-P-81E Alkvd Enamel, 285 TT-P-85E Traffic Paint, 465 TT-P-87D Traffic Paint, 467 TT-P-91D Rubberized Deck Enamel, 469 TT-P-95C Chlorinated Rubber Coating, 567, 921 TT-S-171C Class 2, 926 TT-S-178B Floor Coating, 477

TT-S-223B Waterbase Acrylic Sealer, 382 TT-S-708A Oilbase Wood Stain Exterior, 289 TT-S-711C Oilbase Wood Stain Interior, 291 TT-T-266D Dope and Lacquer Thinner, 1309 TT-T-291F Mineral Spirits, 1315 TT-T-306C Synthetic Resin Thinner, 1333 TT-T-306C Type I, Synthetic Resin Thinner, 1314 TT-T-306E Synthetic Resin Thinner, 1334 TT-T-548D Toluene, 1302, 1326 TT-V-109C Phenolic Spar Varnish, 656 TT-V-119D Phenolic Spar Varnish, 222 TT-V-71H Acrylic Coating Exterior, 354 TT-W-00572 Type Sealer, 927, 1352 TT-X-916 Xylene, 1317

U

Ucryl #3770 Urethane Acrylic Coating, 929 Ucryl #3770 Urethane Acrylic Coating Clear Gloss, 931 Urethane 3-1 Coating, 500 Urethane Acrylic Coating Ucryl #3770 Gloss Clear, 509 U-V Res III Acrylic Epoxy, 933 U-V Res III Epoxy Satin Finish, 935

V

Varnish Fire Resistant Clear, 203, 205 Varnish Gloss Clear Interior, 199 Vinyl Acrylic Ceiling Paint, 159 Vinyl Acrylic Latex Flat, 163, 293 Vinyl Acrylic Primer, 954 Vinyl Enamel System, 571 Vinyl Floor Enamel, 362

W

Waterbase Acrylic Coating, 54, 321 Waterbase Acrylic Enamel ADOT Pole Brown, 523 Waterbase Acrylic Pool Deck Coating, 332 Waterbase Acrylic Sealer, 21, 308, 311, 313, 1295 Waterbase Aluminum Coating, 526 Waterbase Anti-Graffiti Epoxy Coating Clear, 606 Waterbase Concrete Stain, 336 Waterbase Enamel, 295 Waterbase Flat Black, 515, 528 Waterbase Polyurethane Enamel, 532 Waterbase Pool Paint, 1354 Waterbase Silicone Clear Sealer, 1297 Waterbase Traffic Paint, 317 Waterbase Wood Stain, 173 Waterborne 2-Part Aqueous Polyurethane, 386 Waterborne Acrylic Enamel, 330 Waterborne Hydro-Acrylic AG Red Oxide Primer, 1133 Wood Primer Exterior, 1137

Ζ

Zinc Chromate Flat Black Primer, 1009 Zinc Phosphate Alkyd Primer, 1111 Zynolyte Speed Enamel, 939