



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
109 SERIES POLYURETHANE
BRUSHABLE / ROLLABLE
PAGE 1 OF 2

PRODUCT: A two-component commercial grade flooring polyurethane coating for brush and roll application.

DESCRIPTION: Intrepid 109 Series Flooring Polyurethane Coating is a two-component chemically cured product that forms a film that is resistant to chemicals, solvents and abrasion. This product has excellent adhesion to most substrates and is recommended for heavy duty industrial applications where a tough, chemical resistant coating is required. This coating is available in a 2:1 mixture for brush and roll applications. It is specially formulated for ultra high gloss and superior resistance to exterior conditions.

PROPERTIES:

SOLIDS (Weight).....	52 -
59% SOLIDS (Volume).....	40
- 46% VISCOSITY.....	70
- 90 KU COLOR.....	
Full Range POT LIFE (77 degrees F).....	
6 - 8 Hours* TACK	
FREE.....	6 Hours*
RECOAT.....	
Overnight* LIGHT	
SERVICE.....	24 Hours* FULL
SERVICE.....	7 Days*

* Higher temperatures will accelerate dry times and decrease pot life, lower temperatures will lengthen cure times and slightly increase pot life.



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET
109 SERIES POLYURETHANE
BRUSHABLE / ROLLABLE
PAGE 2 OF 2

SURFACE PREPARATION: Surface to be coated must be clean, structurally sound and free of all foreign contaminants including dirt, wax, loose paint or grease. Greasy or oily surfaces should be solvent cleaned with care taken not to paint over moist or wet surfaces. The recommended primer is MIL-P-23377F Type I Epoxy Polyamide. The use of alkyd based primers under this coating is not advisable. Old paint in peeling condition must be removed. Sandblasting or wire brushing are the preferred methods. Chalky paint must also be wire brushed for maximum adhesion.

APPLICATION: Intrepid 109 Series Flooring Polyurethane Coating can be brushed rolled or sprayed. Mechanically mix each component, and then combine at a ratio of 2:1 by volume. Let admixed material stand for 15-30 minutes before using to allow for chemical induction. If thinning is required, use Intrepid MIL-T-81772B TY.I Polyurethane Thinner.

PRECAUTIONS:

USE WITH ADEQUATE VENTILATION.
AVOID CONTACT WITH SKIN AND EYES.
READ MATERIAL SAFETY DATA SHEET BEFORE USING.
KEEP OUT OF THE REACH OF CHILDREN.
FOR INDUSTRIAL USE ONLY.