



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET

MIL-DTL-24607C

NON-FLAMING (INTUMESCENT) ENAMEL

- PRODUCT:** A government specification, non-flaming enamel formulated to meet MIL-DTL-24607C.
- DESCRIPTION:** MIL-DTL-24607C NON-FLAMING ENAMEL is an intumescent, non-flaming coating that is resistant to burning and flaming.
- PROPERTIES:**
- COLORS..... Per Fed-Std
 - 595C FINISH.....
 - Semigloss
 - SOLIDS (Weight)..... 79-
 - 82% PIGMENT (Weight)..... 52
 - 54% VISCOSITY..... 80
 - 90 KU
- DRYING TIMES:**
- TO TOUCH..... 2
 - Hours DRY HARD.....
 - 5 hours
- ADVANTAGES:**
- (1). Non-Flaming (intumescent) Properties
 - (2). Meets MIL-DTL-24607C
 - (3). Resistant to Burning
 - (4). Air Dry Semi-gloss Finish
- USES:**
- (1). Aerospace Applications
 - (2). Submarines
 - (3). Factories
 - (4). Industrial Facilities
- APPLICATION:** Apply by brush, roller or spray methods. For brush and roll, thin with Mineral Spirits Reduce at 10% by volume. For spray application, thin with Xylene at 10-15% by volume. Apply to a dry film thickness of 1.5 - 2.0 mils.

PRECAUTIONS:

KEEP OUT OF REACH OF CHILDREN.
USE WITH ADEQUATE VENTILATION.



TECHNICAL DATA SHEET

AVOID CONTACT WITH SKIN AND EYES.
READ MATERIAL SAFETY DATA SHEET BEFORE USING.
CONTENTS ARE FLAMMABLE.