



# TECHNICAL DATA SHEET

## TECHNICAL DATA SHEET

TT-P-28J Ty. I Cl. 1 Gr. B Comp. 1  
HI-HEAT ALUMINUM COATING  
500A84  
PAGE 1 OF 2

**PRODUCT:** A ready mixed, low VOC, HAP's Free, high heat coating formulated with silicone resin to meet TT-P-28J Ty. I Cl. 1 Gr. B Comp. 1.

**DESCRIPTION:** TT-P-28J Ty. I Cl. 1 Gr. B Comp. 1 is a silicone coating designed to withstand temperatures of up to 1200 degrees Fahrenheit. There must be metal to coating contact between the substrate and the coating. *Do not use a primer.* This coating may be brushed, rolled or sprayed.

**PROPERTIES:** COLORS..... Limited Selection  
FINISH..... Low Sheen  
SOLIDS (Weight)..... 62- 66%  
SOLIDS (Volume)..... 46 - 50%  
VISCOSITY..... 60 - 70 KU

**DRYING TIMES:**

TO TOUCH..... 1 hour  
DRY HARD..... 3 hours  
FULL HARDNESS..... 400 F @ 1 hour

**ADVANTAGES:** (1). High Heat Resistance.  
(2). Silicone Alkyd.  
(3). Durable.  
(4). Air Dry.

**USES:** (1). Aerospace Applications.  
(2). Boilers.  
(3). Heat Exchangers.  
(4). Engines.  
(5). Exhausts.

**APPLICATION:** Apply by brush, roller or spray methods. For brush and roll, thin with Xylene Reducer at 10-15% by volume. For spray application, thin with Toluene at 10-15% by volume.



# TECHNICAL DATA SHEET

## TECHNICAL DATA SHEET

TT-P-28J Ty. I Cl. 1 Gr. B Comp. 1  
HI-HEAT ALUMINUM COATING  
500A81  
PAGE 2 OF 2

### APPLICATION & REDUCTION:

TT-P-28J Ty. I Cl. 1 Gr. B Comp. 1 can be applied by brush, roller or spray. Brush and roll small areas only. Use a natural bristle brush. Do not over brush. Use a short nap mohair roller with a phenolic core. Avoid re-rolling! Thin with Xylene for brush & roll and Toluene or spray application. Spray using conventional or airless equipment with teflon packings. Spray one tack coat followed by one full wet coat to a dry film thickness of 1.5 mils per coat. Two coats are recommended over bare steel.

### SURFACE PREPARATION:

Surface must be clean, dry and free of all contamination before application. Coating must be applied to bare steel. Abrasive blast to a Near White Finish in accordance with SSPC-SP 10 for best results.

### PRECAUTIONS:

Contents are FLAMMABLE.  
Keep away from heat and open flame.  
KEEP OUT OF THE REACH OF CHILDREN!  
Do not take internally.  
Avoid breathing vapor or mist.  
Do not use in tank or pit without proper protection.  
Read Material Safety Data Sheet before use of this product.